

# Product Data Sheet

## Cromadex Liquid Coatings Cromadex 400 Aerosol One Pack Lower Polyurethane Topcoat Aerosol

### Product Description

Cromadex 400 is a one pack lower odour topcoat aerosol for touch up.

Long wet edge  
Exterior durable

Available in 4 gloss levels  
Lead and chromate-free

### Surface Preparation

The surface should be clean, dry and free of grease. Sound existing paintwork should be degreased and abraded with P280 prior to painting.

Cromadex 400 aerosol can be applied over any Cromadex primer aerosol as well as many of the standard liquid primers in the Cromadex range. For further details regarding suitable primers and for larger scale finishing using Cromadex 400, please consult the Cromadex 400 datasheet.

### Application Details

For touch up only

Ideal processing temperature: 15 - 25°C



Shake the aerosol for 2 minutes and spray a sample. Distance to the surface should be approximately 20 centimetres.

A choice of nozzles is available to suit your application. Please consult your local Cromadex Centre for details.

Apply in several thin layers. Before applying the next layer, again shake the aerosol.

### Drying

**Dust Dry** After 15-20 minutes

**Tack Free** After 1-2 hours

**Hardened/ Resprayable** After 12 hours

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the coating applied

### Physical Properties

**Coverage** 1.5 – 2.0 m<sup>2</sup> per aerosol

**VOC** Approx 18% w/w

### Safety Precautions and Disclaimer

**Before using this product please refer to the Cromadex Material Safety Data Sheet.**

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.