

# Product Data Sheet

## Cromadex Liquid Coatings Cromadex 890 Primer Finish Two Pack Non-Isocyanate Acrylic Primer Finish

### Product Description

Cromadex 890 is a two pack gloss primer finish formulated without isocyanate helping to reduce health and safety concerns.

The product contains zinc phosphate giving added corrosion resistance for greater durability, it is also high build making it suitable for application onto blasted steel.

Cromadex 890 is available in full Cromadex range of colours, including BS, RAL, and special matches all in a lead free finish.

### Products and Ancillaries

890 Primer Finish	890 Curing Agent
25-03 Thinner	No 6 Thinner
No 3 Thinner	

### Suitable Substrates and Preparation

Degreasing with Cromadex 678 Spirit Wipe is recommended and should be carried out after any abrasion of the surface

<b>Steel</b>	Degrease and abrade with P180. If necessary blast clean to remove millscale, minimum surface preparation SA2
--------------	--

### Application Details

<b>Mixing Ratio</b>	5 parts 890 Primer Finish 1 part 890 Curing Agent Thinning not normally required, dependent on application equipment	
<b>Pot Life</b>	8 hours @ 20°C (dependent on colour)	
<b>Approved Thickness</b>	75 – 100 microns DFT	155 – 205 microns WFT
<b>Spray Gun</b>	<b>Fluid tip size</b>	<b>Working pressure</b>
<i>Pressure Pot HVLP</i>	1.0 – 1.4 mm	0.7 bar (10 psi)
<i>Airless</i>	9 – 11 thou	2,200 – 2,500 psi
<i>Air Assisted Airless</i>	9 – 11 thou	1,600 – 2,000 psi and 10 – 30 psi air pressure

### Drying and Overcoating

Substrate Temperature	Drying Times		Overcoating Times	
	Touch Dry	Through Dry	Minimum	Maximum
20°C	20 mins	6 hours	Not applicable	
35°C	15 mins	5 hours		
<b>Force Drying</b>	Flash off for 10-15 mins, then 60 – 80°C for 30 mins			
<b>Stoving</b>	Flash off for 10-15 mins, then 120°C for 30 mins			
<b>Full Properties</b>	7 days @ 20°C if air dried, or immediately after stoving			

### Storage and Handling

<b>Storage</b>	Storage should be in accordance with the instructions in Section 7 of the relevant material safety data sheet
<b>Shelf Life</b>	12 months in an unopened, original container from date of mixing at Cromadex centre
<b>Pack Size</b>	5 litres

# Cromadex 890 Primer

## Physical Properties

<b>Volume Solids</b>	49 % (mixed, dependent on colour)	
<b>Colour</b>	Full range available including BS, RAL and special matches – all lead chromate free	
<b>Gloss</b>	Gloss (80%) Measured at 70-75 microns DFT & 60° reflectance <small>A variance of +/-5% may be obtained dependent on application process</small>	
<b>Coverage</b>	6.5 m <sup>2</sup> /l @ 75 microns (dependent on colour), assuming 100% transfer efficiency	
	<b>VOC</b>	<b>Specific Gravity</b>
<b>890 Primer</b>	451 g/l <small>(dependent on colour)</small>	1.31 <small>(dependent on colour)</small>
<b>890 Curing Agent</b>	491 g/l	1.00
<b>25-03 Thinner</b>	873 g/l	0.87
<b>No 6 Thinner</b>	870 g/l	0.87
<b>No 3 Thinner</b>	930 g/l	0.93

## Safety Precautions and Disclaimer

### Before using this product please refer to the Cromadex Material Safety Data Sheet.

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.