

# Product Data Sheet

## Cromadex Liquid Coatings Cromadex Monozinc Aerosol

### Product Description

Cromadex Monozinc is a high quality fast drying zinc spray to treat galvanized and untreated steel. The product is resistant to petrol, chemicals and weather influences.

The product is spot-weldable and has excellent adhesion. Monozinc contains more than 90% Zinc in the dry film.

Monozinc is suitable for overcoating with Cromadex 600, 700 & 800 two pack finishes and 680, 683 & 690 two pack primer finishes only.

### Usage

Before use, carefully read the directions on the packaging and act accordingly.

### Pre-Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetres.

Apply the Monozinc in several thin layers. Before applying the next layer, again shake the aerosol. When desired, after drying, a primer and a lacquer can be applied.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

### Drying

<b>Dust Dry</b>	After 10-15 minutes
<b>Tack Free</b>	After 20-30 minutes
<b>Hardened/Re-Sprayable</b>	After 24 hours

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### Physical Properties

<b>Coverage</b>	1.5 to 2.0 m <sup>2</sup>
<b>Heat Resistant</b>	Up to 350°C
<b>Solid Content</b>	Approx 46% w/w
<b>VOC Content</b>	Approx 54% w/w
<b>Colour</b>	Grey
<b>Pack Size</b>	500 ml

### Safety Precautions and Disclaimer

**Before using this product please refer to the Cromadex Material Safety Data Sheet.**

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.