

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A2201 YZ204I

Product Description

Interpon A2201 clearcoats can be used for pillars and appliqué, roof racks, grille guards, bumpers, and mirror housings, all require protection from the environment as well as being visually harmonious with the overall design of a vehicle. **Interpon A2201** clearcoats are super durable (> two years Florida) and answer to the requested performance level specified by the OEMs. The line of **Interpon A2201** super durable polyester clearcoats (TGIC free) stand ready with excellent appearance and performance.

Product Properties

Chemical type	Polyester super-durable
Area of usage	Automotive trim parts, roof rail systems
Particle Size	Custom manufactured
Appearance	Smooth, matt
Colour	Clear
Gloss (60°)	30 - 35 GU
Density (g/cm³)	1,20 ± 0,05
Stoving schedule	20 min at 190°C (time at object temperature)
Application	electrostatic
Storage stability	under dry, cool (< 25°C) conditions, at least 24 months from production date

Application

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Steel panels, Aluminium
Pretreatment	Bonder (WH/60/OC) iron phosphate, Bonder (722/W/OF) chromate
Film Thickness	70 µm
Cure Schedule	20 minutes at 190°C

Mechanical Tests

Cross Cut Adhesion	DIN EN ISO 2409	Gt 0A
Erichsen	DIN EN ISO 1520	≥ 3 mm
Impact	ASTM D 2794	> 10 ip (reverse)

Corrosion Tests

Salt Spray	DIN EN ISO 9227	240 h corrosion creep < 2 mm from scribe
Humidity Test	DIN EN ISO 6270-2	240 h no blistering

Exterior Durability

Artificial Testing	QUV-B > 50% gloss retention after 500 h
Natural Testing	Florida Exposure > 50% gloss retention after 24 months

Interpon A2201 YZ204I

Pre-treatment

Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of the basecoat and **Interpon A2201** clearcoat. Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate conversion or chromate-free pre-treatment.

Application

Interpon A2201 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924
PO Box 3 www.interpon.com
2170 BA Sassenheim
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon A2201 – YZ204I - Issue #2
Issued: 25.03.2015 Revision Date: 04.06.2015

Interpon®