

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A4740 CZ008Q

Product Description

Interpon A4740 acrylic clearcoat is the OEM standard in the aluminum wheel market. With outstanding application consistency and film performance (approved by all major OEMs) **Interpon A4740** clearcoats are the first choice for wheel makers around the world. **Interpon A4740** acrylic clears combine Class A elegance and OEM specified durability in a super smooth finish with crystal clear transparency.

Powder Properties

Chemistry	GMA Acrylic
Area of usage	Wheels clearcoat
Particle size	Custom manufactured
Appearance	Smooth, glossy
Gloss (60°)	> 90 GU
Density (g/cm³)	1.15 ± 0.05
Storage conditions	≤ 80°F / 27 °C maximum
Shelf life	6 months from production date
Cure schedule	17 minutes at 310°F (time at object temperature)

Test Conditions

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Aluminum
Pretreatment	Chrome conversion, or non-chrome
Film Thickness	2.0 – 4.0 mils
Cure Schedule	17 min at 310°F

Mechanical Tests

Adhesion	ASTM D3359	100%
Hardness	ASTM D3363	H-2H
Flexibility	ASTM D522	1/8" mandrel

Corrosion Tests

CASS Test	GM4476P	240 h corrosion creep < 3 mm max.
Humidity Test	ASTM D2247	240 h, no blistering or loss of gloss

Exterior Durability

Artificial Testing	6000h + KJ Xenon Arc (>90% gloss retention)
Natural Testing	12 month (>90% gloss retention)

OEM Approvals

Chrysler	MS-PA-6-7
General Motors	9985586
Ford Motors	ESA-M2P-109-A2, WSS-M2P-122-C1

Pre-treatment

Aluminum substrate must be clean and free from grease. For maximum protection, it is essential to pre-treat components prior to the application of **Interpon A4740**. OEM aluminum wheels, require a chrome or non-chromate conversion coating prior to application of **Interpon A4740** coatings.

Interpon A4740 CZ008Q

Application

Interpon A4740 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924
PO Box 3 www.interpon.com
2170 BA Sassenheim
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon A4740 - CZ008Q - Issue #3
Issued: 13.03.2015 Revision Date: 20.08.2015

Interpon®