

## **Product Data Sheet**

Product Description	The line of <b>Interpon A4742 polyester clearcoats (TGIC free)</b> stand ready with excellent appearance and performance. Together they are perfectly balanced to provide long lasting protection from chipping scratching, wheel cleaners and corrosive road environments. <b>Interpon A4742 clears</b> have more than 20 years of commercial success that make them the topcoat of choice for aluminium wheels.		
Powder Properties	Chemical type	Polyester	
	Area of usage	Wheels	
	Particle Size	Custom manufactured	
	Appearance	Smooth, glossy	
	Gloss (60°)	<ul> <li>≥ 90 GU</li> <li>1,15 – 1,25</li> <li>10 minutes at 180°C(time at object temperature)</li> <li>electrostatic</li> <li>under dry, cool (≤ 25°C) conditions, at least 24 month from production date</li> </ul>	
	Density (g/cm <sup>3</sup> )		
	Stoving schedule		
	Application		
	Storage Stability		
		stances under which the pro-	n for guidance only. Actual product performance will oduct is used.
			romate
Mechanical Tests	depend upon the circum Substrate Pretreatment Film Thickness	Aluminium Bonder (722/W/OF) Ch 80 - 120 µm	oduct is used.
	depend upon the circum Substrate Pretreatment Film Thickness Cure Schedule Adhesion Erichsen Cupping	Aluminium Bonder (722/W/OF) Ch 80 - 120 µm 10 minutes at 180°C DIN EN ISO 2409 DIN EN ISO 1520	oduct is used. romate Gt 0 ≥ 8mm
Corrosion Tests	depend upon the circum Substrate Pretreatment Film Thickness Cure Schedule Adhesion Erichsen Cupping Impact Salt Spray Humidity Test For maximum protection	Aluminium Bonder (722/W/OF) Ch 80 - 120 µm 10 minutes at 180°C DIN EN ISO 2409 DIN EN ISO 1520 ASTM D 2794 DIN EN ISO 9227 DIN EN ISO 6270-2	oduct is used. romate Gt 0 ≥ 8mm ≥ 20 ip (revers) 240h corrosion creep < 2mm from scribe 240h no blistering or loss of gloss pomponents prior to the application of Interpon 4742
Mechanical Tests Corrosion Tests Pre-treatment Application	depend upon the circum Substrate Pretreatment Film Thickness Cure Schedule Adhesion Erichsen Cupping Impact Salt Spray Humidity Test For maximum protection Aluminium parts require Interpon A4742 powded It is recommended that f	Aluminium Bonder (722/W/OF) Ch 80 - 120 µm 10 minutes at 180°C DIN EN ISO 2409 DIN EN ISO 2409 DIN EN ISO 1520 ASTM D 2794 DIN EN ISO 9227 DIN EN ISO 9227 DIN EN ISO 6270-2 nit is essential to pre-treat co a chromate or chromate-fre	oduct is used. romate Gt 0 ≥ 8mm ≥ 20 ip (revers) 240h corrosion creep < 2mm from scribe 240h no blistering or loss of gloss pomponents prior to the application of Interpon 4742



## Interpon A4742 OZ003GF / 90-80-0016-3

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

 AkzoNobel Powder Coatings B.V.
 T +31 (0)71 308 6981

 Rijksstraatweg 31 (building 24)
 F +31 (0)71 318 6924

 PO Box 3
 www.interpon.com

 2170 BA Sassenheim
 The Netherlands

Copyright © 2015 AkzoNobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel Interpon A4742 - OZ003GF - Issue #3 Issued: 22.01.2015 Revision Date: 10.08.2015

## Interpon.