

# Product Data Sheet

## AkzoNobel Powder Coatings

### Interpon A4742 OZ012GF / 90-80-0016-6

#### Product Description

The line of **Interpon A4742 polyester clearcoats (TGIC free)** stand ready with excellent appearance and performance. Together they are perfectly balanced to provide long lasting protection from chipping, scratching, wheel cleaners and corrosive road environments. **Interpon A4742 clears** have more than 20 years of commercial success that make them the topcoat of choice for aluminium wheels.

#### Powder Properties

<b>Chemical type</b>	Polyester
<b>Area of usage</b>	Wheels
<b>Particle Size</b>	Custom manufactured
<b>Appearance</b>	Smooth, glossy
<b>Gloss (60°)</b>	≥ 90 GU
<b>Density (g/cm<sup>3</sup>)</b>	1,17 ± 0,05
<b>Stoving schedule</b>	10 minutes at 200°C (time at object temperature)
<b>Application</b>	Electrostatic
<b>Storage Stability</b>	Under dry, cool (<25°C) conditions, at least 24 months from production date

#### Test Conditions

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

<b>Substrate</b>	Aluminium
<b>Pretreatment</b>	Bonder (722/W/OF) Chromate
<b>Film Thickness</b>	80 – 120 µm
<b>Cure Schedule</b>	10 minutes at 200°C

#### Mechanical Tests

<b>Adhesion</b>	DIN EN ISO 2409	Gt 0A
<b>Erichsen Cupping</b>	DIN EN ISO 1520	≥ 8 mm
<b>Impact</b>	ASTM D 2794	≥ 20 ip (reverse)

#### Corrosion Tests

<b>Salt Spray</b>	DIN EN ISO 9227	240 h corrosion creep < 2 mm from scribe
<b>Humidity Test</b>	DIN EN ISO 6270-2	240 h no blistering or loss of gloss

#### Pre-treatment

For maximum protection it is essential to pre-treat components prior to the application of **Interpon A4742**. Aluminium parts require a chromate or chromate-free conversion pre-treatment.

#### Application

**Interpon A4742** powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

#### Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

# Interpon A4742

## OZ012GF / 90-80-0016-6

---

### Disclaimer

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

---

**AkzoNobel Powder Coatings B.V.** T +31 (0)71 308 6981  
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924  
PO Box 3 [www.interpon.com](http://www.interpon.com)  
2170 BA Sassenheim  
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel  
Interpon A4742 - OZ012GF - Issue #3  
Issued: 31.01.2014 Revision Date: 08.07.2015

**Interpon**<sup>®</sup>