

# Product Data Sheet

## AkzoNobel Powder Coatings

### Interpon A4742 OZ003GF / 90-80-0016-3

#### Product Description

The line of **Interpon A4742 polyester clearcoats (TGIC free)** stand ready with excellent appearance and performance. Together they are perfectly balanced to provide long lasting protection from chipping, scratching, wheel cleaners and corrosive road environments. **Interpon A4742 clears** have more than 20 years of commercial success that make them the topcoat of choice for aluminium wheels.

#### Powder Properties

<b>Chemical type</b>	Polyester
<b>Area of usage</b>	Wheels
<b>Particle Size Distribution</b>	Custom manufactured
<b>Application</b>	electrostatic
<b>Appearance</b>	Smooth, glossy
<b>Gloss</b>	≥90 [at 60°]
<b>Density (g/cm<sup>3</sup>)</b>	1,15 – 1,25
<b>Stoving schedule</b>	10' / 200°C [time at object temperature]
<b>Storage Stability</b>	Under dry, cool (≤ 25°C) conditions, at least 24 month from production date

#### Test Conditions

The results shown below are based on Bonder 722 yellowchromated aluminium panels coated with approx. 80 – 120µm.

#### Mechanical Tests

<b>Adhesion</b>	DIN EN ISO 2409	Gt 0
<b>Erichsen Cupping</b>	DIN EN ISO 1520	≥ 8mm
<b>Impact</b>	ASTM D 2794	≥ 20 ip (revers)

#### Corrosion Tests

<b>Salt Spray</b>	DIN EN ISO 9227	240h corrosion creep < 2mm from scribe
<b>Humidity Test</b>	DIN EN ISO 6270-2	240h no blistering or loss of gloss

#### Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which AkzoNobel has provided to its customers.

# Interpon A4742

## OZ003GF / 90-80-0016-3

---

### Disclaimer

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

---

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

---

**AkzoNobel Powder Coatings B.V.** T +31 (0)71 308 6981  
24 Rijksweg 31 F +31 (0)71 318 6924  
31 / PO Box 32170 BA www.interpon.com  
Sassenheim  
The Netherlands

Copyright © 2014 AkzoNobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel  
Interpon A4742 - Issue 1  
Issued: 22.01.2015 Revision Date: 22.01.2015

**Interpon**<sup>®</sup>