

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A4742 OZ015GF

Cubatuata

Product Description

The line of **Interpon A4742 polyester clearcoats (TGIC free)** stand ready with excellent appearance and performance. Together they are perfectly balanced to provide long lasting protection from chipping, scratching, wheel cleaners and corrosive road environments. **Interpon A4742 clears** have more than 20 years of commercial success that make them the topcoat of choice for aluminium wheels.

Powder Properties

Chemical type	Polyester		
Area of usage	Wheels		
Particle Size	Custom manufactured		
Appearance	Smooth, glossy		
Gloss (60°)	≥ 90 GU		
Density (g/cm ³)	1,15 – 1,30		
Stoving schedule	10 minutes at 190°C (time at object temperature)		
Application	Electrostatic		
Storage Stability	Under dry, cool (≤ 25°C) conditions, at least 24 month from production date		

Test Conditions

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Aluminium		
Pretreatment	Bonder (722/W/OF) Chromate		
Film Thickness	70 μm		
Cure Schedule	10 minutes at 190°C		
Adhesion Erichsen Cupping Impact	DIN EN ISO 2409 DIN EN ISO 1520 ASTM D 2794	Gt 0 ≥ 8mm ≥ 20 ip (reverse)	
Salt Spray Humidity Test	DIN EN ISO 9227 DIN EN ISO 6270-2	240h corrosion creep < 2mm from scribe 240h no blistering or loss of gloss	

Corrosion Tests

Pre-treatment

Mechanical Tests

For maximum protection it is essential to pre-treat components prior to the application of **Interpon A4742**. Aluminium parts require a chromate or chromate-free conversion pre-treatment.

Application

Interpon A4742 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which AkzoNobel has provided to its customers.



1

Interpon A4742 OZ015GF

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924
PO Box 3 www.interpon.com
2170 BA Sassenheim
The Netherlands

