

Product Data Sheet

AkzoNobel Powder Coatings

Interpon 610 AC

Product Description

Interpon 610 AC powder coatings are part of the Interpon 610 range and maintain all of the film performance attributes of polyester chemistry but are designed to offer users significant improvements in their application characteristics. They can be sprayed on conventional equipment and are compatible with standard powders but give a more uniform coverage, and in particular give improved coverage in Faraday Cage areas. Powders are available in a range of colours in gloss and reduced gloss finishes, and are always custom matched to the user's requirements.

Powder Properties

Chemical type	Polyester TGIC-free
Particle Size	Suitable for electrostatic spray
Specific gravity	1.2-1.8 g/cm ³ depending on colour
Storage	Dry cool conditions below 25°C
Shelf life	12 months
Stoving schedule (object temperature)	15 minutes at 190°C 10 minutes at 200°C 8 minutes at 210°C

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Gold Seal polished steel
Pretreatment	Gold Seal lightweight Zinc Phosphate
Film Thickness	50 microns
Stoving Schedule	10 minutes at 200°C (object temperature)

Mechanical Tests

Flexibility (Conical Mandrel)	ISO 6860	Pass 3mm
Adhesion (2mm Crosshatch)	ISO 2409	Gt0
Erichsen Cupping	ISO 1520	Pass 7mm
Hardness	ISO2815 (2000gms)	Pass - no penetration to substrate
Impact	ISO 6272	50kgcm

Chemical and Durability Tests

Salt Spray (250 hours)	ISO 7253	No corrosion creep >2mm from scribe. Class 0. No change of visual appearance
Cyclic Humidity (1000 hours)	BS3900-F2	No corrosion creep >2mm from scribe. Class 0. No change of visual appearance
Distilled Water Immersion (240 hours)	BS3900-F7	Pass - no blistering or loss of gloss
Exterior Durability	Excellent - no chalking, slight loss of gloss after 12 months continuous exposure but no film breakdown or reduction in protective properties	
Chemical Resistance	Generally good resistance to acids, alkalis and oils at normal temperatures	

Interpon 610 AC

Pre-treatment

Aluminium, steel or Zintec surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminium substrates may require a chromate conversion coating.

Application

Interpon 610 AC powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Additional Information

Interpon 610 AC High Reactivity (HR) powders are also available for use where a lower oven temperature or shorter curing time is required.

Stoving schedule	15 minutes at 160°C
(object temperature)	8 minutes at 180°C
Storage	Dry cool conditions below 25°C
Shelf life	12 months

For further details on powder properties and film performance of Interpon 610 AC (HR) please contact AkzoNobel.

Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
24 Rijksweg 31 F +31 (0)71 318 6924
31 / PO Box 32170 BA www.interpon.com
Sassenheim
The Netherlands

Copyright © 2014 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon 610 AC - Issue 1
Issued: 01.12.2014 Revision Date: 01.12.2014

Interpon®