

# Product Data Sheet

## AkzoNobel Powder Coatings

### Interpon A5150 MP7354

#### Product Description

**Interpon A5150** is a series of standard durability powder coatings, formulated without TGIC, designed for exterior exposure. Tested against OEM specifications **Interpon A5150** exhibits excellent corrosion resistance and good gloss retention and resistance to colour change. **Interpon A5150** has been developed for chassis and chassis components for trucks.

#### Powder Properties

<b>Chemical type</b>	Polyester
<b>Area of usage</b>	Truck chassis and chassis parts
<b>Particle Size</b>	Custom manufactured
<b>Appearance</b>	Smooth, satin
<b>Colour</b>	MB7350
<b>Gloss (60°)</b>	60 ± 5 GU
<b>Density (g/cm<sup>3</sup>)</b>	1,30 ± 0,05
<b>Stoving schedule</b>	15 minutes at 180°C (time at object temperature)
<b>Application</b>	Electrostatic
<b>Storage stability</b>	Under dry, cool (< 27°C, 80°F) conditions, at least 18 months from production date

#### Comments

**MP7354** is designed for chassis (P4) to fulfill the requirements of the following specification; "TL004-05 Surface and Coating Quality - Powder Coating"

#### Test Conditions

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

<b>Substrate</b>	Gold seal polished steel panels
<b>Pretreatment</b>	Zinc phosphate
<b>Film Thickness</b>	85 ± 5 µm
<b>Cure Schedule</b>	15 minutes at 180°C

#### Mechanical Tests

<b>Flexibility</b>	ISO6860	≤ 3 mm
<b>Adhesion</b>	DIN EN ISO 2409	Gt 0
<b>Erichsen Cupping</b>	DIN EN ISO 1520	≥ 8 mm
<b>Buchholz Hardness</b>	ISO 2815	≥ 80
<b>Impact</b>	ISO 6272	≥ 9 Nm (reverse)
<b>Impact</b>	ISO 6272	≥ 9 Nm (direct)

#### Corrosion Tests

<b>Neutral Salt Spray</b>	ASTM B117	504 h corrosion creep < 2 mm from scribe
<b>Humidity Test</b>	ISO 6270	504 h no blistering

#### Exterior Durability

Excellent-no chalking, slight loss of gloss after 12 months, continuous exposure but no film breakdown or reduction in protective properties

# Interpon A5150 MP7354

---

## Chemical Resistance

Very good resistance to acids, alkalis and oils at normal temperatures

---

## Pre-treatment

Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of **Interpon A5150**. Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate conversion or chromate-free pre-treatment

---

## Application

**Interpon A5150** powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

---

## Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

---

## Disclaimer

**IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.**

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

---

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981  
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924  
PO Box 3 www.interpon.com  
2170 BA Sassenheim  
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel  
Interpon A5150 – MP7354 – Issue #2  
Issued: 26.08.2015 Revision Date: 07.09.2015

**Interpon**<sup>®</sup>