

Product Data Sheet

AkzoNobel Powder Coatings

Interpon 620 AM

OA260E

Matt White

Product Description

OA260E is a Polyester based powder coating, formulated without the use of TGIC, offering the benefits of **Interpon 620** in combination with specific antimicrobial activity.

Interpon 620 AM powders are available in a full range of colours, in gloss, reduced gloss, texture and other special finishes or can be customer matched to the user's requirements.

Powder Properties

Chemical type	Polyester
Particle Size	Suitable for electrostatic spray
Specific gravity	1,5 – 1,6 g/cm ³
Film Thickness	50 – 70 microns
Storage	Dry cool conditions below 25°C (open boxes must be resealed)
Shelf life	12 months
Sales Code	OA260E
Stoving schedule (object temperature)	15 - 30 minutes at 190°C 10 – 20 minutes at 200°C 8 - 16 minutes at 210°C

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Mechanical tests : Gold Seal Polished steel Chemical & Durability tests : Gold Seal Lightweight Steel
Pretreatment	Zinc Phosphate
Film Thickness	50 – 70 microns
Stoving Schedule	10 minutes at 200°C (object temperature)

Mechanical Tests

	[test]	[results]
Adhesion	ISO 2409 (2 mm crosshatch)	GTO
Flexibility	ISO 6860 (conical mandrel)	3mm
Impact (direct/reverse)	ASTM D2794	25/25 kgcm
Ericksen Cupping	ISO 1520	>7 mm
Hardness	ISO 1518 (4000g)	No penetration to substrate

Chemical and Durability Tests

Salt Spray (250 hours)	ASTM B117	No corrosion creep >2mm from scribe. No blistering.
Cyclic Humidity	BS3900-F2	No blistering or loss of gloss
Distilled water immersion	ISO 2182	No blistering or loss of gloss
Chemical Resistance	Generally good resistance to acids, alkalis and oils at room temperature.	
Exterior Durability	Excellent – no chalking slight loss of gloss after 12 months continuous exposure but no film breakdown or reduction in protective properties	

Interpon 620 AM OA260E Matt White

Pre-treatment

Aluminium, Steel or Zintec surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight Zinc phosphating or ferrous metals improved corrosion resistance. Aluminium substrates may require a chromate conversion coating.

Application

Interpon 620 AM powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that powder film thickness be between 60 – 110 microns. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Additional Information

Interpon 620 AM in conjunction with BioCote Ltd © has been tested for antimicrobial efficacy in accordance with ISO 22196:2011 and exhibited a minimum of 95% and up to 99.99% reduction in the population of Escheria Coli and Methicillin Resistant Staphylococcus Aureus (MRSA). Testing was carried out by an independent laboratory and is classified as “microbiological results satisfactory”. BioCote silver ion technology has been proven effective against the following bacteria in Laboratory conditions.

Multi Drug Resistant Bacteria

ESBL Erischeria coli
CRE Klebsiella pneumoniae
MRSA Methicillin Resistant Staphylococcus Aureus
VRE Vancomycin Resistant Enterococcus

Bacteria

Acinetobacter baumannii
Bacillus subtilis
Campylobacter coli
Campylobacter jejuni
Clostridium difficile (excluding spore form)
Escherichia coli O 157
Enterbacter aerogenes
Enterococcus faecalis
Legionella pneumophila
Listeria monocytogenes
Pseudomonas auruginosa
Salmonella enteritidis
Salmonella typhimurium
Shigella spp.
Staphylococcus aureus
Staphylococcus epidermidis
Streptococcus faecalis

Interpon 620 AM contains BioCote silver phosphate glass antimicrobial technology to preserve the coating surface and prevent degradation caused by microbial growth once applied to the intended substrate.

Safety Precautions

Please consult the Material Safety Datasheet (MSDS).

Disclaimer

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
24 Rijksweg F +31 (0)71 318 6924
31 / PO Box 32170 BA www.interpon.com
Sassenheim
The Netherlands

Copyright © 2014 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
OA260E - Issue 3
Issued: Nov.2014

Interpon®