

# Product Data Sheet

## AkzoNobel Powder Coatings

### Interpon HT 550 WN303JR

#### Product Description

Interpon HT 550, WN303JR, provides corrosion protection and appearance integrity for high temperature components such as exhaust manifold and mufflers that are made of aluminized steel substrates. The temperature capability and performance of the Standard High Temperature Paints are limited by the melting point (660°C, 1220°F) of the aluminium coating on the aluminized steel.

#### Powder Properties

<b>Gloss (60°)</b>	5-15
<b>Density</b>	2.1 ± 0.1 g/cm <sup>3</sup>
<b>Storage</b>	Dry cool conditions
<b>Shelf life</b>	Under dry, cool (<25°C) conditions 6 months at least
<b>Stoving schedule</b> (object temperature)	20 minutes at 210°C
Failure to observe the correct curing conditions may cause difference in color, gloss and the deterioration of the coating properties.	

#### Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

<b>Substrate</b>	Type 1 Aluminized steel panels (ASTM A463)
<b>Film Thickness</b>	45-65 µm
<b>Stoving Schedule</b>	20 minutes at 210°C (object temperature)

#### Mechanical Tests

<b>Flexibility</b>	ASTM-D522 (Conical Mandrel)	N/A
<b>Adhesion</b>	ASTM-D3359 (2 mm Crosscut)	4B min
<b>Recoatability</b>	ASTM-D3359 (2 mm Crosscut)	Not recommended
<b>Hardness</b>	ASTM-D3363 (Gouge)	2H

#### Other Tests

<b>Salt Spray</b>	(UNI ISO 9227/93)	>500 hrs
<b>Thermal Exposure</b> (350°C for 120 hours)		Slight loss of gloss and hue (DE<1), neither cracking no film detachment, it keeps good adhesion properties (GT0)
<b>Thermal Exposure</b> (500°C for 2 hours)		Loss of gloss and color, neither cracking not film detachment, it keeps good adhesion properties

#### Pre-treatment

All oil and grease, scale, rust, dirt and process markings such as grease pencil or chalk must be removed. A multi-stage cleaning including a conversion coating is recommended for optimum performance

## Interpon HT 550 WN303JR

---

### Application

WN303JR powders can be applied by manual or automatic electrostatic spray equipment. Recommended film thickness is 45 – 65 µm (1.8-2.5mils). For more detailed information please contact AKZONOBEL technical service team.

---

### Additional Information

Interpon HT550, WN303JR, was formerly known as MOR-TEMP™ MUFLER BLACK, 321MT97001

---

### Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

---

### Disclaimer

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

---

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981  
24 Rijksweg 31 F +31 (0)71 318 6924  
31 / PO Box 32170 BA www.interpon.com  
Sassenheim  
The Netherlands

Copyright © 2014 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel  
Interpon HT 550 WN303JR - Issue 1  
Issued: 25.02.2015 Revision Date: 25.02.2015

**Interpon**®